

**ORIGINAL PATENT APPLICATION BASED ON:**

**Docket:** 80914RLO

**Inventor(s):** Jiann H. Chen

Joseph A. Pavlisko

Charles E. Hewitt

Robert A. Lancaster

**Attorney:** Raymond L. Owens

**FUSER MEMBER OVERCOATED WITH FLUOROCARBON-SILICONE**  
**RANDOM COPLOYMER CONTAINING ALUMINUM OXIDE**

**EXPRESS MAIL LABEL NO.: EL485195456US**

**Date of Mailing:** 4/24/00

**FUSER MEMBER OVERCOATED WITH FLUOROCARBON-SILICONE**

**RANDOM COPOLYMER CONTAINING ALUMINUM OXIDE**

**CROSS REFERENCE TO RELATED APPLICATION**

Reference is made to commonly-assigned U.S. Patent Application  
Serial No. \_\_\_\_\_, filed concurrently herewith, entitled "Fluorocarbon-  
Silicone Random Copolymer For Use in Toner Release Layer" by Chen et al, the  
disclosure of which is incorporated herein by reference.

**FIELD OF THE INVENTION**

This invention relates to fuser members useful for heat-fixing a  
heat-softenable toner material to a substrate. More particularly, the invention  
relates to materials usable as a toner release layer in a fuser member.

**BACKGROUND OF THE INVENTION**

Heat-softenable toners are widely used in imaging methods such as  
electrostatography, wherein electrically charged toner is deposited imagewise on a  
dielectric or photoconductive element bearing an electrostatic latent image. Most  
often in such methods, the toner is then transferred to a surface of another  
substrate, such as, a receiver sheet comprising paper or a transparent film, where it  
is then fixed in place to yield the final desired toner image.

When heat-softenable toners, comprising, thermoplastic polymeric  
binders, are employed, the usual method of fixing the toner in place involves  
applying heat to the toner once it is on the receiver sheet surface to soften it and  
then allowing or causing the toner to cool.

One such well-known fusing method comprises passing the toner-  
bearing receiver sheet through the nip formed by a pair of opposing rolls, at least  
one of which (usually referred to as a fuser roll) is heated and contacts the toner-  
bearing surface of the receiver sheet in order to heat and soften the toner. The  
other roll (usually referred to as a pressure roll) serves to press the receiver sheet  
into contact with the fuser roll. In some other fusing methods, the configuration is  
varied and the "fuser roll" or "pressure roll" takes the form of a flat plate or belt.

The description herein, while generally directed to a generally cylindrical fuser roll  
in combination with a generally cylindrical pressure roll, is not limited to fusing

systems having members with those configurations. For that reason, the term "fuser member" is generally used herein in place of "fuser roll" and the term "pressure member" in place of "pressure roll."

5 The fuser member usually comprises a rigid core covered with a resilient material, which will be referred to herein as a "base cushion layer." The resilient base cushion layer and the amount of pressure exerted by the pressure member serve to establish the area of contact of the fuser member with the toner-bearing surface of the receiver sheet as it passes through the nip of the fuser member and pressure members. The size of this area of contact helps to establish the length of time that any given portion of the toner image will be in contact with and heated by the fuser member. The degree of hardness (often referred to as "storage modulus") and stability thereof, of the base cushion layer are important factors in establishing and maintaining the desired area of contact.

10 In some previous fusing systems, it has been advantageous to vary the pressure exerted by the pressure member against the receiver sheet and fuser member. This variation in pressure can be provided, for example in a fusing system having a pressure roll and a fuser roll, by slightly modifying the shape of the pressure roll. The variance of pressure, in the form of a gradient of pressure that changes along the direction through the nip that is parallel to the axes of the rolls, can be established, for example, by continuously varying the overall diameter of the pressure roll along the direction of its axis such that the diameter is smallest at the midpoint of the axis and largest at the ends of the axis, in order to give the pressure roll a sort of "bow tie" or "hourglass" shape. This will cause the pair of rolls to exert more pressure on the receiver sheet in the nip in the areas near the ends of the rolls than in the area about the midpoint of the rolls. This gradient of pressure helps to prevent wrinkles and cockle in the receiver sheet as it passes through the nip. Over time, however, the fuser roll begins to permanently deform to conform to the shape of the pressure roll and the gradient of pressure is reduced or lost, along with its attendant benefits. It has been found that permanent deformation (alternatively referred to as "creep") of the base cushion layer of the fuser member is the greatest contributor to this problem.

Particulate inorganic fillers have been added to base cushion layers to improve mechanical strength and thermal conductivity. High thermal conductivity is advantageous when the fuser member is heated by an internal heater, so that the heat can be efficiently and quickly transmitted toward the outer surface of the fuser member and toward the toner on the receiver sheet it is intended to contact and fuse. High thermal conductivity is not so important when the roll is intended to be heated by an external heat source.

Optimal metal-particle filled elastomer fuser members have long been sought. At one time, it was predicted that:

10           “The metal of the metal-containing filler dispersed in the elastomer may be easily selected by one skilled in the art without undue experimentation by testing the metal-containing filler, such as a metal, metal alloy, metal oxide, metal salt or other metal compound, in an elastomer. The general classes of metals which are applicable to the present invention include those metals of Groups Ib, 2; 15   2b, 3; 3b, 4a, 4b, 5; 5b, 6b, 7b, 8 and the rare earth elements of the Periodic Table.” (U.S. Patent No. 4,264,181 to Lentz et al, column 10, lines 42-53; also U.S. Patent No. 4,272,179 to Seanor, column 10, lines 45-54.)

This prediction of easy selection of the metal for a metal-containing filler is not correct in view of subsequent work.

20           A metal-containing filler which provides good results in one elastomer may provide very poor results in another elastomer, even if the elastomers are very similar.

U.S. Patent No. 4,515,884 to Field et al, discloses a fuser member which utilizes metal oxide filled polydimethylsiloxane. The metal oxides are iron oxide and tabular alumina. Calcined alumina is described as being unsuitable per se. (column 9, line 50-column 10, line 47).

25           In U.S. Patent No. 4,264,181 to Lentz et al, good results were obtained when lead oxide was used as a filler in various fluorocarbon elastomers (Viton E430, Viton E605C, Viton GH<sup>TM</sup>; Examples X, XI, XII). In U.S. Patent

No. 5,017,432 to Eddy et al, on the other hand, teaches that oxide fluorocarbon elastomers (for example, Viton GF<sup>TM</sup>) would produce an unacceptable fuser member. In fluoroelastomers, cupric oxide is preferred.

U.S. Patent No. 4,272, 179 to Seanor and U.S. Patent Nos. 4,264,181 and 4,257,699 to Lentz teach the use, as a release oil, of a polydimethylsiloxane that incorporates mercapto functional groups. These patents indicate that lead oxide filler in the outer elastomer release layer interacts with the mercapto functionalized PDMS fluid to yield a release film on the surface of the fuser member.

Preparation of metal containing elastomers remains problematic. U.S. Patent No. 4,515,884 to Field et al, and U.S. Patent No. 5,017,432 to Eddy et al, cite large numbers of critical features or important aspects of their metal containing elastomers: choice of material (Field, column 9, lines 50-65 and column 10, lines 24-25), interaction of filler surface and elastomer (Field, column 9, lines 32-65), particle size (Field, column 10, lines 1-8 and lines 25-30; Eddy, column 9, line 65—column 10, line 3), concentration of metal-filler (Field, column 10, lines 9-23 and lines 31-47), capability of interacting with functional groups of release agent (Eddy, column 9, lines 26-30), reactivity of the metal filler with the elastomer (Eddy, column 9, lines 33-43), and acid-base characteristics of the metal filler (Eddy, column 9, lines 43-56). The lists of critical features and important aspects in Field and Eddy do not fully correlate. It is unknown whether this difference represents real differences in material characteristics or only differences in techniques and analysis.

In electrophotographic fuser systems, fuser members are commonly made with an overcoat release layer of polysiloxane elastomer, polyfluorocarbon resin, or polyfluorocarbon elastomer.

Polysiloxane elastomers have relatively high surface energy and relatively low mechanical strength, but are adequately flexible and elastic and can produce high quality fused images. After a period of use, however, the self release property of the roller degrades and offset begins to occur. Application of a

polysiloxane fluid during roller use enhances the ability of the roller to release toner, but shortens roller life due to oil absorption. Oiled portions tend to swell and wear and degrade faster.

One type of material that has been widely employed in the past to  
5 form a resilient base cushion layer for fuser rolls is condensation-crosslinked siloxane elastomer. Disclosure of filled condensation-cured poly(dimethylsiloxane) "PDMS" elastomers for fuser rolls can be found, for example, in U.S. Patent Nos. 4,373,239; 4,430,406; and 4,518,655. U.S. Patent No. 4,970,098 to Ayala-Esquillin et al teaches a condensation cross-linked  
10 diphenylsiloxane-dimethylsiloxane elastomer having 40 to 55 weight percent zinc oxide, 5 to 10 weight percent graphite, and 1 to 5 weight percent ceric dioxide.

A widely used siloxane elastomer is a condensation-crosslinked PDMS elastomer, which contains about 32-37 volume percent aluminum oxide filler and about 2-6 volume percent iron oxide filler, and is sold under the trade  
15 name, EC4952, by the Emerson Cummings Co., U.S.A. It has been found that fuser rolls containing EC4952 cushion layers exhibit serious stability problems over time of use, i.e., significant degradation, creep, and changes in hardness, that greatly reduce their useful life. Mechanical Energy Resolver (MER) test results correlate with and thus accurately predict the instability exhibited during actual  
20 use. Nevertheless, materials such as EC4952 initially provide very suitable resilience, hardness, and thermal conductivity for fuser roll cushion layers. See U.S. Patent No. 5,595,823.

U.S. Patent No. 5,582,917 discloses toner fusing members which have a substrate coated with a fluorocarbon-silicone polymeric composition.  
25 Although these toner fusing members have proved effective they have a problem in that there can be toner contamination and may have a problem with low thermal conductivity. The advantage of using the fluorocarbon random copolymer containing aluminum oxide is that the aluminum oxide have been added to improve the thermal conductivity.

U.S. Patent No. 5,595,823 discloses toner fusing members which have a substrate coated with a fluorocarbon random copolymer containing aluminum oxide. Although these toner fusing members have proved effective and desirable thermal conductivity, they have a problem in that there can be toner contamination. The advantage of using the fluorocarbon silicone compositions is that they are effective for use with toner release agents which typically include silicone.


It would be desirable to provide a fuser member with an overcoat layer includes aluminum oxide filler and polyfunctional siloxane polymer to have a high thermal conductivity and low toner contamination.

### SUMMARY OF THE INVENTION

It is an object of the invention to provide materials for forming a toner release layer.

It is another object of the present invention to provide a fuser member which makes use of fluorocarbon silicone but which has improved toner release and mechanical strength.

These objects are achieved by a fuser member comprising a core and a layer overlying the core, the layer including a fluorocarbon random copolymer, a curing agent which cures the fluorocarbon random copolymer, the cured fluorocarbon random copolymer having subunits of:



wherein

x is from 30 to 90 mole percent,

y is from 10 to 70 mole percent,

z is from 0 to 34 mole percent;

x + y + z equals 100 mole percent;

the layer further including a particulate filler having aluminum oxide and alkaline earth metal oxides or alkaline earth metal hydroxides or combinations thereof; and

a siloxane polymer comprising one or more curable, silanol-terminated, polyfunctional poly(C1-6 alkyl)siloxane polymers.

It is a feature of the present invention that a fuser member formed with a toner release layer that includes a metal oxide filled polyfluorocarbon elastomer has a moderate surface energy and that by using a fluorocarbon-silicone polymeric composition an improved fuser member is provided. Aluminum oxide  
5 filler and siloxane polymer when added to the claimed combination provide improved thermal conductivity and reduce toner contamination.

A further advantage of the present invention is particular fillers such as inorganic base have been added to the fluorocarbon random copolymer in the presence of bisphenol curing agent to improve the mechanical strength.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a cross sectional view of a fusing member in accordance with the present invention.

### DETAILED DESCRIPTION OF PARTICULAR EMBODIMENTS

FIG. 1 shows a cross sectional view of a fuser member 10 which  
15 include a fuser roller, pressure roller, oiler donor roller, oiler metering roller, or pre-conditioning roller, etc. The core 16 is usually metallic, such as stainless steel, steel, aluminum, etc.; however, the core 16 may also be made of a ceramic or plastic. The primary requisites for core 16 materials are that it provide the necessary stiffness, be able to support the force placed upon it, and be able to  
20 withstand whatever temperature to which it is subjected. Disposed above the core 16 lies one or more optional intermediate layers 14 which are characterized in the art as cushion layers. The outermost layer 12 is a toner release layer. In the event that a cushion layer 14 is desired, then the outermost layer 12 is disposed directly over the core 16. The outermost layer 12 is the toner release layer, it includes a  
25 curing agent and a fluorocarbon random copolymer that is cured by the curing agent, the fluorocarbon random copolymer has subunits of:

- (CH<sub>2</sub> CF<sub>2</sub>)<sub>x</sub>— (vinylidene fluoride subunit ("VF<sub>2</sub>")),
- (CF<sub>2</sub>CF(CF<sub>3</sub>)<sub>y</sub>— (hexafluoropropylene subunit ("HFP")), and
- (CF<sub>2</sub> CF<sub>2</sub>)<sub>z</sub>—(tetrafluoroethylene subunit ("TFE"))



wherein

x is from 30 to 90 mole percent,

y is from 10 to 70 mole percent,

z is from 0 to 34 mole percent; and

x + y + z equals 100 mole percent;

the layer further including particulate filler having aluminum oxide;

and

a siloxane polymer comprising one or more curable, silanol-terminated, polyfunctional poly(C1-6 alkyl)siloxane polymers.

It is a feature of the present invention that a fuser member formed with a toner release layer that includes a metal oxide filled polyfluorocarbon elastomer has a moderate surface energy and that by using a fluorocarbon-silicone polymeric composition an improved fuser member is provided. Aluminum oxide filler and siloxane polymer when added to the claimed combination provide improved thermal conductivity and reduce toner contamination.

In these formulas, x, y, and z are mole percentages of the individual subunits relative to a total of the three subunits (x+y+z), referred to herein as "subunit mole percentages" (The curing agent can be considered to provide an additional "cure-site subunit", however, the contribution of these cure-site subunits is not considered in subunit mole percentages.) In the fluorocarbon copolymer, x has a subunit mole percentage of from 30 to 90 mole percent, y has a subunit mole percentage of from 10 to 70 mole percent, and z has a subunit mole percentage of from 0 to 34 mole percent. In a currently preferred embodiment of the invention, subunit mole percentages are: x is from 40 to 80, y is from 10 to 60, and z is from 0 to 34; or more preferably x is from 42 to 75, y is from 14 to 58, and z is 0. In the currently preferred embodiments of the invention, x, y, and z are selected such that fluorine atoms represent at least 70 percent of the total formula weight of the VF<sub>2</sub>, HFP, and TFE subunits.

Preferably, curable polyfunctional poly(C1-6 alkyl)siloxane polymers are also used in the present invention and are cured concurrently with the fluorocarbon random copolymer when cured by the curing agent to produce a

coating suitable for use as the toner release layer of a fusing member. In accordance with the invention, coated fusing members have low energy surfaces which release toner images with minimal offset. These coatings can also be advantageously used with small amounts of externally added polymeric release agents, for example mercapto functionalized polydimethylsiloxanes, to further minimize offset. Preferred curable polyfunctional poly(C1-6 alkyl)siloxane polymers are heat-curable silicones, however peroxide-curable silicones can also be used with conventional initiators. Heat-curable silicones include the hydroxy-functionalized polyfunctional organopolysiloxanes belonging to the class of silicones known as "soft" silicones. Preferred soft silicones are silanol-terminated polyfunctional organopolysiloxanes containing repeating units of the formula,

$$(R1)_a SiO_{(4-a)/2}$$

wherein R1 is C1-6 alkyl and a is 0 to 3. Alkyl groups which R1 can represent include methyl, ethyl, propyl, isopropyl, butyl, sec. butyl, pentyl and hexyl. Preferred soft silicones are those in which R1 is methyl. The soft silicones can be used singly or as mixtures of silicones and can contain various proportions of mono-, di-, tri- and tetra-functional siloxane repeating units. Preferred soft silicones comprise a major component of a silanol- or trimethylsilyl-terminated polydimethylsiloxane having a number average molecular weight between about 20,000 to 300,000 and a minor component of a polymethylsiloxane comprising monofunctional and tetrafunctional siloxane repeating units and having a number average molecular weight in the range of 1,000 to 10,000. Exemplary soft silicones are commercially available or can be prepared by conventional methods, for example, SFR-100 silicone (sold by General Electric Co.) and EC 4952 silicone (sold by Emerson Cummings Co.). SFR-100 silicone is characterized as a silanol- or trimethylsilyl-terminated polymethylsiloxane and is a liquid blend comprising about 60-80 weight percent of a difunctional polydimethylsiloxane having a number average molecular weight of about 150,000, and 20-40 weight percent of a polytrimethylsilyl silicate resin having monofunctional (i.e. trimethylsiloxane) and tetrafunctional (i.e. SiO<sub>2</sub>) repeating units in an average

ratio of between about 0.8 and 1 to 1 and having a number average molecular weight of about 2,200. EC 4952 silicone is characterized as a silanol-terminated polymethylsiloxane having about 85 mole percent of difunctional dimethylsiloxane repeating units, about 15 mole percent of trifunctional methylsiloxane repeating units and having a number average molecular weight of about 21,000. Other polyfunctional poly(C1-6 alkyl)siloxane polymers which can be used are disclosed in U.S. Patent Nos. 4,387,176 and 4,536, 529, the disclosures of which are hereby incorporated by reference.

In one aspect of the invention a fluorocarbon-silicone composite is obtained which can be used as a fusing roll layer without adding release agents and without causing offset. Suitable fluorocarbon random copolymers are the terpolymers of vinylidene fluoride, hexafluoropropylene and tetrafluorethylene having a fluorine content of at least about 70 mole percent as disclosed in U.S. Patent No. 5,035,950. The silicone component of the composite is a soft silicone, for example, a polymethylsiloxane composition such as SFR-100 silicone.

Preferred composites of the invention have a ratio of siloxane polymer to fluorocarbon copolymer between about 0.1 and 3 to 1 by weight, preferably between about 0.2 and 0.5 to 1. The composite is preferably obtained by curing a mixture comprising from about 50-70 weight percent of a fluorocarbon copolymer, 10-30 weight percent of a curable polyfunctional polymethylsiloxane polymer, most preferably about 20-30 weight percent. 1-10 weight percent of a fluorocarbon-curing agent, 1-3 weight percent of a fluorocarbon-curing accelerator, 8-30 weight percent of an acid acceptor type filler, and 10-30 weight percent of an inert filler.

Curing of the composite is carried out according to the well known conditions for curing vinylidene fluoride based copolymers ranging, for example, from about 12- 48 hours at temperatures of between 50°C. to 250°C. Preferably the coated composition is dried until solvent free at room temperature, then gradually heated to about 230 °C. over 24 hours, then maintained at that temperature for 24 hours.

The outer layer includes particulate filler comprising aluminum oxide and additional particulate selected from alkaline earth metal oxides, alkaline earth metal hydroxides, and combinations of alkaline earth metal oxides and hydroxides. In a currently preferred embodiment of the invention, the additional  
5 particulate is a mixture of magnesium oxide and calcium hydroxide. The particulate filler has a total concentration in the outer layer of from about 13 to 170 parts per hundred parts by weight of the fluorocarbon random copolymer (pph). The aluminum oxide has a concentration of from about 10 to 140 parts per hundred parts ( pph) by weight of the fluorocarbon random copolymer.  
10 Concentrations of aluminum oxide of less than 10 parts by weight may not provide the degree of stability desired to the layer. Concentrations of aluminum oxide of greater than 140 parts by weight will render the layer too hard to provide the desired area of contact with the toner-bearing receiver sheet. In a particular embodiment of the invention, the outer layer has 3 pph of MgO, 6 pph of  
15  $\text{Ca(OH)}_2$  and from 10 to 140 pph of aluminum oxide.

The aluminum oxide particles employed as filler in the base cushion layer of a fuser member of the invention can be obtained from any convenient commercial source, e.g., Magnesium Electron, Inc. of Flemington, N.J. The particle size does not appear to be critical. Particle sizes anywhere in the range of  
20 0.1 to 100 micrometers have been found to be acceptable. In the examples presented below the aluminum oxide particles were from 1 to 40 micrometers in diameter.

To form the outer layer, the filler particles are mixed with the uncured polymer, crosslinking agent, and any other additives, such as an  
25 accelerator; shaped over the base cushion, and cured. The fluorocarbon is cured by crosslinking with basic nucleophile addition curing. Basic nucleophilic cure systems are well known and are discussed, for example, in U.S. Patent No. 4,272,179. One example of such a cure system combines a bisphenol as the crosslinking agent and an organophosphonium salt, as an accelerator.

The crosslinker is incorporated into the polymer as a cure-site subunit, for example, bisphenolic residues. Other examples of nucleophilic addition cure systems are sold commercially as DIAK No. 1 (hexamethylenediamine carbamate) and DIAK No. 3 (N,N'-dicinnamylidene-1,6-hexanediamine) by E.I. duPont de Nemours & Co.

Suitable uncured polymers are available commercially. In a particular embodiment of the invention, a vinylidene fluoride-co-hexafluoropropylene was used which can be represented as  $-(VF)(75)-(HFP)(25)-$ . This material is marketed by E.I. duPont de Nemours and Company under the designation "Viton A" and is referred to herein as "Viton A". In another embodiment of the invention, a vinylidene fluoride-co-hexafluoropropylene was used which can be represented as  $-(VF)(42)-(HFP)(58)-$ . This material is marketed by Minnesota Mining and Manufacturing, St. Paul, Minn, under the designation "Fluorel FX-2530" and is referred to herein as "FX-2S30". Other suitable uncured vinylidene fluoride-cohexafluoropropylenes and vinylidene fluoride-co-tetrafluoroethylene-cohexafluoropropylenes are available, for example, Fluorel FX-9038.

The molecular weight of the uncured polymer is largely a matter of convenience, however, an excessively large or excessively small molecular weight would create problems, the nature of which are well known to those skilled in the art. In a preferred embodiment of the invention the uncured polymer has a number average molecular weight in the range of about 100,000 to 200,000.

The fuser member is constructed forming a toner release layer on a overlying an optional base cushion provided on a core comprising the steps of:

- 25 (a) providing a core;  
(b) providing a mixture having:  
(i) a fluorocarbon random copolymer having subunits

of:



Sub  
A3

wherein

x is from 30 to 90 mole percent,

y is from 10 to 70 mole percent,

z is from 0 to 34 mole percent;

5 x + y + z equals 100 mole percent;

(ii) a particular fillers comprising aluminum oxide and additional particulate selected from alkali metal oxides, alkali metal hydroxides, and combinations of alkali metal oxides and hydroxides; and

(iii) a crosslinking agent and a crosslinking accelerator; and a siloxane polymer comprising one or more curable, silanol-terminated, polyfunctional poly(C1-6 alkyl)siloxane polymers, the siloxane polymer comprising at least two different functional siloxane units selected from the group consisting of monofunctional, difunctional, trifunctional and tetrafunctional siloxane units, and creating an interpenetrating network consisting essentially of  
10 separately crosslinked polymers, the fluorocarbon random copolymer and the fluorocarbon curing agent forming one crosslinked polymer, and the siloxane  
15 polymer forming a second crosslinked polymer; and

(c) applying the mixture to the base cushion and curing the applied mixture to crosslink the fluorocarbon random copolymer.

20 In cases where it is intended that the fuser member be heated by an internal heater, it is desirable that the outer layer have a relatively high thermal conductivity, so that the heat can be efficiently and quickly transmitted toward the outer surface of the fuser member that will contact the toner intended to be fused. (Depending upon relative thickness, it is generally even more desirable that the  
25 base cushion layer and any other intervening layers have a relatively high thermal conductivity. Suitable materials for the base cushion layer are discussed below).

Some fusing systems use a release oil, such as a PDMS oil, to prevent offset, that is, to aid the roll in releasing from the toner it contacts during the fusing operation. During use, the oil is continuously coated over the surface of  
30 the fuser member in contact with the toner image. The fuser member of the invention can be used with polydimethylsiloxane, amino functionalized

polydimethylsiloxane or mercapto functionalized polydimethylsiloxane release oils at normally used application rates or at reduced application rates, from about 0.5 mg/copy to 10 mg/copy (the copy is 8.5 by 11 inch 20 pound bond paper.)

The outer layer of the fuser member of the invention is  
5 substantially resistant to release oil induced swelling. In a preferred embodiment of the invention, the change in size due to swelling is less than 0.1 to 1.0 percent. In an even more preferred embodiment of the invention, the change in size due to swelling is less than 0.01 to 0.1 percent.

The thickness of the base cushion and outer layers and the  
10 composition of the base cushion layer can be chosen so that the base cushion layer can provide the desired resilience to the fuser member, and the outer layer can flex to conform to that resilience. The thickness of the base cushion and outer layers will be chosen with consideration of the requirements of the particular application intended. Usually, the outer layer would be thinner than the base cushion layer.  
15 For example, base cushion layer thickness in the range from 0.6 to 5.0 mm have been found to be appropriate for various applications. In some embodiments of the present invention, the base cushion layer is about 2.5 mm thick, and the outer layer is from about 25 to 30 mm thick.

Suitable materials for the base cushion layer include any of a wide  
20 variety of materials previously used for base cushion layers, such as the condensation cured polydimethylsiloxane marketed as EC4952 by Emerson Curning. An example of a condensation cured silicon rubber base cushion layer is GE 4044 marketed by General Electric of Waterford, N.Y. An example of an addition cured silicone rubber is Silastic J RTV marketed by Dow Corning applied  
25 over a silane primer DC-1200 also marketed by Dow Corning.

In a particular embodiment of the invention, the base cushion is resistant to cyclic stress induced deformation and hardening. Such materials when subjected to cyclic stress using an MER, as above discussed, exhibit changes in length and hardness (storage modulus) of less than about 20 percent. Examples of  
30 suitable materials are filled condensation-crosslinked PDMS elastomers disclosed in U.S. Patent No. 5,269,740 (copper oxide filler), U.S. Patent No. 5,292,606 (zinc

oxide filler), U.S. Patent No. 5,292,562 (chromium oxide filler), U.S. Patent No. 5,480,724 (tin oxide filler), U.S. Patent No. 5,336,539 (nickel oxide filler). These materials all show reasonable heat conductivities and much less change in hardness and creep than EC4952 or the PDMS elastomer with aluminum oxide  
5 filler. Additional suitable base cushions are disclosed in U.S. Patent Nos. 5,466,533, 5,474,852; and 5,464,703, the disclosures of which are hereby incorporated herein by reference.

The core of the fuser member is usually cylindrical in shape. It comprises any rigid metal or plastic substance. Metals are preferred when the  
10 fuser member is to be internally heated, because of their generally higher thermal conductivity. Suitable core materials include, e.g., aluminum, steel, various alloys, and polymeric materials such as thermoset resins, with or without fiber reinforcement. The core can be a support which has been conversion coated and primed with metal alkoxide primer in accordance with U.S. Patent No. 5,474,821,  
15 which is hereby incorporated by reference.

The fuser member is mainly described herein in terms of embodiments in which the fuser member is a fuser roll having a core, a base cushion layer overlying the core, and an outer layer superimposed on the base cushion. The invention is not, however, limited to a roll, nor is the invention  
20 limited to a fusing member having a core bearing two layers: the base cushion layer and the outer layer. The fuser member of the invention can have a variety of outer configurations and layer arrangements known to those skilled in the art. For example, the base cushion layer could be eliminated or the outer layer described herein could be overlaid by one or more additional layers.

25 The invention is further illustrated by the following Examples and Comparative Examples.

### EXAMPLES 1-3

A cylindrical stainless steel core was cleaned with dichloromethane and dried. The core was then primed with a uniform coat of a metal alkoxide type  
30 primer, Dow 1200 RTV Prime Coat primer, marketed by Dow Corning Corporation of Midland, Mich.; which contains: light aliphatic petroleum naptha



(85 weight percent), tetra (2-methoxyethoxy)-silane (S weight percent), tetrapropyl orthosilicate (5 weight percent), and tetrabutyl titanate (5 weight percent). Silastic.RTM. J RTV room temperature vulcanizing silicone rubber, marketed by Dow Corning Corporation of Midland, Mich.; was then mixed with catalyst and injection molded onto the core and cured at 232°C. for 2 hours under 75 tons/inch<sup>2</sup> of pressure. The roller was then removed from the mold and baked in a convection oven with a temperature ramp increasing to 23°C. substantially uniformly over 24 hours and then maintaining that temperature for an additional 24 hours. After air cooling, EC4952 marketed by Emerson Cumming Division of W. R. Grace and Co. of Connecticut was blade coated directly onto the Silastic J layer, then cured for 12 hours at about 210°C., followed by 48 hours at 218°C. in a convection oven. After air cooling, the EC4952 was ground to a thickness of 20 mils. The cured EC4952 was corona discharged for 15 minutes at 750 watts and an outer layer was applied.

Fluorocarbon random copolymer and soft silicone SFR-100 was mixed as indicated in Table 1 with varying amounts of aluminum oxide. Viton A is a commercially available fluorocarbon random copolymer which is sold by duPont Corporation. Column 2 sets forth the parts per hundred (pph) of a fluorocarbon random copolymer. The weight fraction of fluorocarbon random copolymer and soft silicone SFR-100 was held constant. Each of the formulations was mixed with 2.5g of Viton Curative 20 and 6g of Viton curative 30 (products made by the duPont Corporation). The formulations were all mixed on a two-roll mill then dissolved to form a 25 weight percent solids solution in methyl ethyl ketone. Part of the resulting material was ring coated onto the cured EC4952 layer, air dried for 16 hours, baked with 24 hour ramp to 260°C. and then a 24 hour soak at 260°C. The Silastic J layer had a thickness of 380 mils. The resulting outer layer of fluorocarbon random copolymer had a thickness of 1 mil. The remainder of the material was cast to a film and allowed to dry for 3 days. Afterwards the cast films were baked with 24 hour ramp to 260°C. and then a 24 hour soak at 260°C.

**Table 1**

	Viton A	pph / SFR-100	pph / Al <sub>2</sub> O <sub>3</sub>
E1	100	20	10
E2	100	20	50
E3	100	20	140

**COMPARATIVE EXAMPLES 1-5**

Substantially the same procedures were followed as in Examples 1-3, except that in lieu either of SFR-100 or aluminum oxide or none of both was added as indicated in Table 2.

**Table 2**

	Viton A	pph / SFR-100	pph / Al <sub>2</sub> O <sub>3</sub>
C1	100	20	0
C2	100	0	0
C3	100	0	10
C4	100	0	50
C5	100	0	140

**Materials Testing**

Thermal conductivity of thin film is measured by Thermal Conductivity Analyzer TCA-100 ( HOLOMETRIX) by the guarded heat flow meter method in accordance with ASTM F433-77. Results are shown in Table 3.

**Table 3**

<u>Sample</u>	<u>pph / Al<sub>2</sub>O<sub>3</sub></u>	<u>K</u>
E1	10	0.0828
E2	50	0.1406
E3	140	0.1962
C1	0	0.0837
C2	0	0.0837
C3	10	0.1061
C4	50	0.2043
C5	140	0.2758

Table 3 shows that the presence of the aluminum oxide increases the thermal conductivity both of the fluorocarbon- silicone random copolymer and the fluorocarbon random copolymer.

5

#### **Toner Release Test**

The test samples are employed to evaluate the toner offset and release force characteristics of the fuser member coating. Two samples are cut approximately 1-inch square of each example. One of these squares is left untreated by release agent (the dry sample). To the surface of the other sample is applied in unmeasured amount of Xerox amino-functionalized PDMS 8R79.

10

Each sample is incubated overnight at a temperature of 175°C. Following this treatment, the surface of each sample is wiped with dichloromethane. Each sample is then soaked in dichloromethane for one hour and allowed to dry before off-line testing for toner offset and release properties.

15

Each sample is tested in the following manner:

A one-inch square of paper covered with unfused polyester toner is placed in contact with a sample on a bed heated to 175°C, and a pressure roller set for 80 psi is locked in place over the laminate to form a nip. After 20 minutes the roller is released from the laminate.

The extent of offset for each sample is determined by microscopic examination of the sample surface following delamination. The following numerical evaluation, corresponding to the amount of toner remaining on the surface, is employed.

1	0% offset
2	1-20% offset
3	21-50% offset
4	51-90% offset
5	91-100% offset

5. Qualitative assessment of the force required for delamination of the from the samples is as follows:

1	low release force
2	moderate release force
3	high release force

Results are shown in Table 4.

**Table 4**

Sample	Dry Offset	Dry Release	Amino Offset	Amino Release
E1	0.6	2	0.2	1
E2	2	2	1	1
E3	1	2	0.2	1
C3	0.3	2	0.2	1
C4	3	2	1.5	1
C5	3	2	0.2	1

- 10 Table 4 shows a comparison between the fluorocarbon- silicone random copolymer and the fluorocarbon random copolymer when the aluminum oxide was added into both of the polymers. In terms of the toner release and offset, the fluorocarbon-silicone random copolymer shows the significantly improvement in the dry toner release and amino offset.

- 15 The above data and description show that the combination of aluminum oxide in conjunction with the fluorocarbon- silicone random copolymer

shows significant improvement of attainable properties. The positive attributes such as the increased thermal conductivity are maximized while negative attributes such as propensity to offset, lack of release are minimized. Aluminum oxide filler and siloxane polymer when added to the claimed combination provide  
5 improved thermal conductivity and reduce toner contamination.

The invention has been described in detail with particular reference to certain preferred embodiments thereof, but it should be appreciated that variations and modifications can be effected within the scope of the invention.

1  
2  
3  
4  
5  
6  
7  
8  
9  
10  
11  
12  
13  
14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100  
101  
102  
103  
104  
105  
106  
107  
108  
109  
110  
111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000  
1001  
1002  
1003  
1004  
1005  
1006  
1007  
1008  
1009  
1010  
1011  
1012  
1013  
1014  
1015  
1016  
1017  
1018  
1019  
1020  
1021  
1022  
1023  
1024  
1025  
1026  
1027  
1028  
1029  
1030  
1031  
1032  
1033  
1034  
1035  
1036  
1037  
1038  
1039  
1040  
1041  
1042  
1043  
1044  
1045  
1046  
1047  
1048  
1049  
1050  
1051  
1052  
1053  
1054  
1055  
1056  
1057  
1058  
1059  
1060  
1061  
1062  
1063  
1064  
1065  
1066  
1067  
1068  
1069  
1070  
1071  
1072  
1073  
1074  
1075  
1076  
1077  
1078  
1079  
1080  
1081  
1082  
1083  
1084  
1085  
1086  
1087  
1088  
1089  
1090  
1091  
1092  
1093  
1094  
1095  
1096  
1097  
1098  
1099  
1100  
1101  
1102  
1103  
1104  
1105  
1106  
1107  
1108  
1109  
1110  
1111  
1112  
1113  
1114  
1115  
1116  
1117  
1118  
1119  
1120  
1121  
1122  
1123  
1124  
1125  
1126  
1127  
1128  
1129  
1130  
1131  
1132  
1133  
1134  
1135  
1136  
1137  
1138  
1139  
1140  
1141  
1142  
1143  
1144  
1145  
1146  
1147  
1148  
1149  
1150  
1151  
1152  
1153  
1154  
1155  
1156  
1157  
1158  
1159  
1160  
1161  
1162  
1163  
1164  
1165  
1166  
1167  
1168  
1169  
1170  
1171  
1172  
1173  
1174  
1175  
1176  
1177  
1178  
1179  
1180  
1181  
1182  
1183  
1184  
1185  
1186  
1187  
1188  
1189  
1190  
1191  
1192  
1193  
1194  
1195  
1196  
1197  
1198  
1199  
1200  
1201  
1202  
1203  
1204  
1205  
1206  
1207  
1208  
1209  
1210  
1211  
1212  
1213  
1214  
1215  
1216  
1217  
1218  
1219  
1220  
1221  
1222  
1223  
1224  
1225  
1226  
1227  
1228  
1229  
1230  
1231  
1232  
1233  
1234  
1235  
1236  
1237  
1238  
1239  
1240  
1241  
1242  
1243  
1244  
1245  
1246  
1247  
1248  
1249  
1250  
1251  
1252  
1253  
1254  
1255  
1256  
1257  
1258  
1259  
1260  
1261  
1262  
1263  
1264  
1265  
1266  
1267  
1268  
1269  
1270  
1271  
1272  
1273  
1274  
1275  
1276  
1277  
1278  
1279  
1280  
1281  
1282  
1283  
1284  
1285  
1286  
1287  
1288  
1289  
1290  
1291  
1292  
1293  
1294  
1295  
1296  
1297  
1298  
1299  
1300  
1301  
1302  
1303  
1304  
1305  
1306  
1307  
1308  
1309  
1310  
1311  
1312  
1313  
1314  
1315  
1316  
1317  
1318  
1319  
1320  
1321  
1322  
1323  
1324  
1325  
1326  
1327  
1328  
1329  
1330  
1331  
1332  
1333  
1334  
1335  
1336  
1337  
1338  
1339  
1340  
1341  
1342  
1343  
1344  
1345  
1346  
1347  
1348  
1349  
1350  
1351  
1352  
1353  
1354  
1355  
1356  
1357  
1358  
1359  
1360  
1361  
1362  
1363  
1364  
1365  
1366  
1367  
1368  
1369  
1370  
1371  
1372  
1373  
1374  
1375  
1376  
1377  
1378  
1379  
1380  
1381  
1382  
1383  
1384  
1385  
1386  
1387  
1388  
1389  
1390  
1391  
1392  
1393  
1394  
1395  
1396  
1397  
1398  
1399  
1400  
1401  
1402  
1403  
1404  
1405  
1406  
1407  
1408  
1409  
1410  
1411  
1412  
1413  
1414  
1415  
1416  
1417  
1418  
1419  
1420  
1421  
1422  
1423  
1424  
1425  
1426  
1427  
1428  
1429  
1430  
1431  
1432  
1433  
1434  
1435  
1436  
1437  
1438  
1439  
1440  
1441  
1442  
1443  
1444  
1445  
1446  
1447  
1448  
1449  
1450  
1451  
1452  
1453  
1454  
1455  
1456  
1457  
1458  
1459  
1460  
1461  
1462  
1463  
1464  
1465  
1466  
1467  
1468  
1469  
1470  
1471  
1472  
1473  
1474  
1475  
1476  
1477  
1478  
1479  
1480  
1481  
1482  
1483  
1484  
1485  
1486  
1487  
1488  
1489  
1490  
1491  
1492  
1493  
1494  
1495  
1496  
1497  
1498  
1499  
1500  
1501  
1502  
1503  
1504  
1505  
1506  
1507  
1508  
1509  
1510  
1511  
1512  
1513  
1514  
1515  
1516  
1517  
1518  
1519  
1520  
1521  
1522  
1523  
1524  
1525  
1526  
1527  
1528  
1529  
1530  
1531  
1532  
1533  
1534  
1535  
1536  
1537  
1538  
1539  
1540  
1541  
1542  
1543  
1544  
1545  
1546  
1547  
1548  
1549  
1550  
1551  
1552  
1553  
1554  
1555  
1556  
1557  
1558  
1559  
1560  
1561  
1562  
1563  
1564  
1565  
1566  
1567  
1568  
1569  
1570  
1571  
1572  
1573  
1574  
1575  
1576  
1577  
1578  
1579  
1580  
1581  
1582  
1583  
1584  
1585  
1586  
1587  
1588  
1589  
1590  
1591  
1592  
1593  
1594  
1595  
1596  
1597  
1598  
1599  
1600  
1601  
1602  
1603  
1604  
1605  
1606  
1607  
1608  
1609  
1610  
1611  
1612  
1613  
1614  
1615  
1616  
1617  
1618  
1619  
1620  
1621  
1622  
1623  
1624  
1625  
1626  
1627  
1628  
1629  
1630  
1631  
1632  
1633  
1634  
1635  
1636  
1637  
1638  
1639  
1640  
1641  
1642  
1643  
1644  
1645  
1646  
1647  
1648  
1649  
1650  
1651  
1652  
1653  
1654  
1655  
1656  
1657  
1658  
1659  
1660  
1661  
1662  
1663  
1664  
1665  
1666  
1667  
1668  
1669  
1670  
1671  
1672  
1673  
1674  
1675  
1676  
1677  
1678  
1679  
1680  
1681  
1682  
1683  
1684  
1685  
1686  
1687  
1688  
1689  
1690  
1691  
1692  
1693  
1694  
1695  
1696  
1697  
1698  
1699  
1700  
1701  
1702  
1703  
1704  
1705  
1706  
1707  
1708  
1709  
1710  
1711  
1712  
1713  
1714  
1715  
1716  
1717  
1718  
1719  
1720  
1721  
1722  
1723  
1724  
1725  
1726  
1727  
1728  
1729  
1730  
1731  
1732  
1733  
1734  
1735  
1736  
1737  
1738  
1739  
1740  
1741  
1742  
1743  
1744  
1745  
1746  
1747  
1748  
1749  
1750  
1751  
1752  
1753  
1754  
1755  
1756  
1757  
1758  
1759  
1760  
1761  
1762  
1763  
1764  
1765  
1766  
1767  
1768  
1769  
1770  
1771  
1772  
1773  
1774  
1775  
1776  
1777  
1778  
1779  
1780  
1781  
1782  
1783  
1784  
1785  
1786  
1787  
1788  
1789  
1790  
1791  
1792  
1793  
1794  
1795  
1796  
1797  
1798  
1799  
1800  
1801  
1802  
1803  
1804  
1805  
1806  
1807  
1808  
1809  
1810  
1811  
1812  
1813  
1814  
1815  
1816  
1817  
1818  
1819  
1820  
1821  
1822  
1823  
1824  
1825  
1826  
1827  
1828  
1829  
1830  
1831  
1832  
1833  
1834  
1835  
1836  
1837  
1838  
1839  
1840  
1841  
1842  
1843  
1844  
1845  
1846  
1847  
1848  
1849  
1850  
1851  
1852  
1853  
1854  
1855  
1856  
1857  
1858  
1859  
1860  
1861  
1862  
1863  
1864  
1865  
1866  
1867  
1868  
1869  
1870  
1871  
1872  
1873  
1874  
1875  
1876  
1877  
1878  
1879  
1880  
1881  
1882  
1883  
1884  
1885  
1886  
1887  
1888  
1889  
1890  
1891  
1892  
1893  
1894  
1895  
1896  
1897  
1898  
1899  
1900  
1901  
1902  
1903  
1904  
1905  
1906  
1907  
1908  
1909  
1910  
1911  
1912  
1913  
1914  
1915  
1916  
1917  
1918  
1919  
1920  
1921  
1922  
1923  
1924  
1925  
1926  
1927  
1928  
1929  
1930  
1931  
1932  
1933  
1934  
1935  
1936  
1937  
1938  
1939  
1940  
1941  
1942  
1943  
1944  
1945  
1946  
1947  
1948  
1949  
1950  
1951  
1952  
1953  
1954  
1955  
1956  
1957  
1958  
1959  
1960  
1961  
1962  
1963  
1964  
1965  
1966  
1967  
1968  
1969  
1970  
1971  
1972  
1973  
1974  
1975  
1976  
1977  
1978  
1979  
1980  
1981  
1982  
1983  
1984  
1985  
1986  
1987  
1988  
1989  
1990  
1991  
1992  
1993  
1994  
1995  
1996  
1997  
1998  
1999  
2000  
2001  
2002  
2003  
2004  
2005  
2006  
2007  
2008  
2009  
2010  
2011  
2012  
2013  
2014  
2015  
2016  
2017  
2018  
2019  
2020  
2021  
2022  
2023  
2024  
2025  
2026  
2027  
2028  
2029  
2030  
2031  
2032  
2033  
2034  
2035  
2036  
2037  
2038  
2039  
2040  
2041  
2042  
2043  
2044  
2045  
2046  
2047  
2048  
2049  
2050  
2051  
2052  
2053  
2054  
2055  
2056  
2057  
2058  
2059  
2060  
2061  
2062  
2063  
2064  
2065  
2066  
2067  
2068  
2069  
2070  
2071  
2072  
2073  
2074  
2075  
2076  
2077  
2078  
2079  
2080  
2081  
2082  
2083  
2084  
2085  
2086  
2087  
2088  
2089  
2090  
2091  
2092  
2093  
2094  
2095  
2096  
2097  
2098  
2099  
2100  
2101  
2102  
2103  
2104  
2105  
2106  
2107  
2108  
2109  
2110  
2111  
2112  
2113  
2114  
2115  
2116  
2117  
2118  
2119  
2120  
2121  
2122  
2123  
2124  
2125  
2126  
2127  
2128  
2129  
2130  
2131  
2132  
2133  
2134  
2135  
2136  
2137  
2138  
2139  
2140  
2141  
2142  
2143  
2144  
2145  
2146  
2147  
2148  
2149  
2150  
2151  
2152  
2153  
2154  
2155  
2156  
2157  
2158  
2159  
2160  
2161  
2162  
2163  
2164  
2165  
2166  
2167  
2168  
2169  
2170  
2171  
2172  
2173  
2174  
2175  
2176  
2177  
2178  
2179  
2180  
2181  
2182  
2183  
2184  
2185  
2186  
2187  
2188  
2189  
2190  
2191  
2192  
2193  
2194  
2195  
2196  
2197  
2198  
2199  
2200  
2201  
2202  
2203  
2204  
2205  
2206  
2207  
2208  
2209  
2210  
2211

- |    |                    |
|----|--------------------|
| 10 | fuser member       |
| 12 | outermost layer    |
| 14 | intermediate layer |
| 16 | core               |

[illegible]